



Azkoitia Plant

MILL TEST CERTIFICATE

ISO 9001 - ISO/TS 16949

EA-TIDE
QC1

Product Made in Spain

CUSTOMER: ENERGY ALLOYS HOUSTON	WORKS REFERENCE: 1760585
REFERENCE: 1054934 OP	SALES ORDER: 276734-2
PRODUCT NR: 959	HEAT NUMBER: 629928
	ROLLED: 07.11.2014
	MASTER REFERENCE: 186858

REQUIRED PRODUCT			
9%Cr 1%Mo ROUND BARS AS ROLLED Q+T+STRESS RELIEVED 2.25" ASTM A-29 (*)			
3.000/8.000 mm RANDOM			
EXPEDITION	DELIVERY: 0080486315	WEIGHT (KG): 4.925	BUNDLES: 2
			UNITS: 35

MADE ACCORDING TO			
ASTM A370 13 15.11.2013 ; ASTM A29-A29M E1 . . .2012			
ENERGY ALLOYS EAGL-600 05 06.04.2013 ; API SPEC 6A 20*ED.+ER1&2+AD12.3 . .03.2013			
NACE MR0175/ISO 15156-1 2*EDICION 15.10.2009			
NACE MR0175/ISO 15156-2 2*EDICION 15.10.2009 ; EN 10204 :2004 OCT. 2004 3.1			

CHEMICAL ANALYSIS OF HEAT								
								U: % HEAT NUMBER: 629928
	C	Mn	Si	P	S	Cr	Ni	Mo
min.	0,090	0,300	0,250			8,000		0,900
Max.	0,150	0,600	1,000	0,020	0,010	10,000	0,500	1,100
cer.	0,106	0,426	0,707	0,011	0,006	8,602	0,236	0,955
								0,118

MECHANICAL PROPERTIES AS SUPPLIED (CONDITIONS)	
Temperature of: (1): Austenitizing 1.796 °F ; Time: (1): 120 Minutes ; Cooling: (1): OIL 78°F	
Temperature of: (2): Tempering 1.310 °F ; Time: (2): 120 Minutes ; Cooling: (2): Air	
Temperature of: (3): Stress Relieved 1.220 °F ; Time: (3): 360 Minutes	
MECHANICAL PROPERTIES AS SUPPLIED (TEST)	
Specimen Test location: At 1/2 radius ; Standard (ASTM A370 13 15.11.2013)	
Ts (>= 100 KSI): 108 KSI	
Ys(1) (Rp(0,2%) 80/95 KSI): Rp(0,2%) 85 KSI ; Ys(2) ((0,5%) 80/95 KSI): (0,5%) 88 KSI	
El. (2 " >= 20 %) : 2 " 25,2 % ; Z (>= 40 %) : 68 %	
Observations: Re(0,2%) metodo "OFFSET" y Re(0,5%) metodo "EUL" ; Standard (ASTM E23-01A E12007)	
Notch impact sample direction (Longitudinal): Longitudinal	
Notch Impact sample type (CHARPY-V): CHARPY-V ; Notch Impact test Temperature (75 °F): 75 °F	
K(1): 111 Ft.Lb ; K(2): 110 Ft.Lb ; K(3): 112 Ft.Lb ; K (average) (>= 40 Ft.Lb): 111 Ft.Lb	
Lateral expansion: 1.61-1.63-1.60 mm ; Shear value: 70-70-70 % ; Standard (ASTM E18-2008B)	
Surface hardness (HB): 238 HB ; Hardness at 1/2 radius(1) (16/22 HRC): 20,5 HRC	
Hardness at 1/2 radius(2) (207/235 HB): 230 HB	
Notch impact sample direction (Longitudinal): Longitudinal	
Notch Impact sample type (CHARPY-V): CHARPY-V ; Notch Impact test Temperature (14 °F): 14 °F	
K(1): 75 Ft.Lb ; K(2): 76 Ft.Lb ; K(3): 73 Ft.Lb ; K (average) (>= 29 Ft.Lb): 74,67 Ft.Lb	
Lateral expansion: 0.98-0.99-0.97 mm ; Shear value: 60-60-60 %	

ADDITIONAL TESTS	
Standard (ASTM E112-01.10.2013) ; Grain size: Austenitic 6/7	

NON DESTRUCTIVE TESTS	
Internal defects standard(1) (ASTM A388-A388M-...2011) ; Internal defects type/method (PSL3)	
Internal defects standard(2) (API SPEC 6A20*ED.+ER1&2+AD12.3 . .03.2013)	
ULTRASONIC INSPECTION 100% : O.K.	

ADDITIONAL INFORMATION	
Reduction ratio: 82,9 ; MADE IN ELECTRIC FURNACE AND VACUUM DEGASSED. ; Energy Alloys EAGL-600 REV5	

TECHNOLOGY & QUALITY CERTIFIES THAT THE PRODUCT FULL FILLS THE ORDER'S SPECIFICATION	
APPROVED BY: ANGEL FUNES EXPOSITO	SIGN:
DATE: 02.12.2014	
REF.: 2000820050000	Analyst of Quality certificates



MILL TEST CERTIFICATE

Azkoitia Plant

ISO 9001 - ISO/TS 16949



Product Made in Spain

CUSTOMER: ENERGY ALLOYS HOUSTON		WORKS REFERENCE: 1760585
REFERENCE: 1054934 OP	SALES ORDER: 276734-2	HEAT NUMBER: 629928
PRODUCT NR: 959	MASTER REFERENCE: 186858	ROLLED: 07.11.2014

"Cold rotary straightening" ; FURNACE CALIBRATION ACCORDING TO AMS-MIL-H-6875, AMS-2750
TREATMENT OF THE MATERIAL IN CONVENTIONAL FURNACE

Material melted and manufactured 100% in Spain through the Electric Arc Furnace and Vacuum Degassing route.
Steel not exposed to Mercury, or to any other metal alloy that is liquid, at ambient temperatures during processing or while in Gerdau's possession.
Steel is free from Uranium or any other harmful radioactive contamination.
Steel products were not repaired by welding.
100% anti mix test performed by spectrometry.