

## MILL TEST CERTIFICATE

Basauri Plant

ISO 9001 - ISO/TS 16949

2" BAKER RETAINER 9CR




Product Made in Spain

|   |                          |
|---|--------------------------|
| CUSTOMER: HOWCO METALS MANAGEMENT PTE LTD | WORKS REFERENCE: 1740628 |
| REFERENCE: HOU-111769                     | SALES ORDER: 273719-7    |
| PRODUCT NR:                               | HEAT NUMBER: 629109      |
| MASTER REFERENCE: 192526                  | ROLLED: 03.07.2014       |

|  |                      |                    |            |
|--|----------------------|--------------------|------------|
| REQUIRED PRODUCT   |                      |                    |            |
| 9%Cr 1%Mo ROUND BARS TURNED Q+T+STRESS RELIEVED 1.5" SPECIFICATION'S TOLERANCE |                      |                    |            |
| 3.000/8.000 mm RANDOM  |                      |                    |            |
| EXPEDITION   | DELIVERY: 0080480201 | WEIGHT (KG): 5.392 | BUNDLES: 2 |
|  |                      |                    | UNITS: 81  |

|   |  |  |  |
|---|--|--|--|
| MADE ACCORDING TO   |  |  |  |
| SAE-AMS 2301 K 08.2010 ; HOWCO HG001 2.20.02.2014 ; HOWCO HG 9CR BAR 3.18.06.2012   |  |  |  |
| EN ISO 9001 2008/AC:2009 29.07.2009 ; NACE MR0175/ISO 15156-2 2ª EDICION 15.10.2009 |  |  |  |
| NACE MR0175/ISO 15156-1 2ª EDICION 15.10.2009 ; EN 10204 :2004 OCT. 2004 3.1        |  |  |  |

|                           |        |       |       |       |       |        |       |       |       |                          |        |
|---------------------------|--------|-------|-------|-------|-------|--------|-------|-------|-------|--------------------------|--------|
| CHEMICAL ANALYSIS OF HEAT |        |       |       |       |       |        |       |       |       | U: % HEAT NUMBER: 629109 |        |
|                           | C      | Mn    | Si    | P     | S     | Cr     | Ni    | Mo    | Cu    | Ti                       | B      |
| Min.                      | 0,090  | 0,300 | 0,250 |       |       | 8,000  |       | 0,900 |       |                          |        |
| Max.                      | 0,150  | 0,600 | 1,000 | 0,020 | 0,010 | 10,000 | 0,500 | 1,100 | 0,250 |                          |        |
| Cer.                      | 0,100  | 0,421 | 0,629 | 0,010 | 0,001 | 8,559  | 0,175 | 0,971 | 0,108 | 0,0010                   | 0,0013 |
| Nb                        |        |       |       |       |       |        |       |       |       |                          |        |
| Min.                      |        |       |       |       |       |        |       |       |       |                          |        |
| Max.                      |        |       |       |       |       |        |       |       |       |                          |        |
| Cer.                      | 0,0010 |       |       |       |       |        |       |       |       |                          |        |



|   |  |  |  |  |  |  |  |  |  |  |  |
|---|--|--|--|--|--|--|--|--|--|--|--|
| INCLUSIONS (MICROINCLUSIONS)  |  |  |  |  |  |  |  |  |  |  |  |
| Standard (ASTM E452013. . . 2013) ; Type/method (D Tabla I-r) ; A(t):0,5 ; A(h):0 ; B(t):1 ; B(h):0 |  |  |  |  |  |  |  |  |  |  |  |
| C(t):0 ; C(h):0 ; D(t):0,5 ; D(h):0   |  |  |  |  |  |  |  |  |  |  |  |
| INCLUSIONS (MACROINCLUSIONS)  |  |  |  |  |  |  |  |  |  |  |  |
| Standard (SAE-AMS 2301K08.2010) ; Severity(1):Mean value 0 ; Severity(2):Individual value 0,1       |  |  |  |  |  |  |  |  |  |  |  |
| Frequency(1):Mean value 0 ; Frequency(2):Individual value 0,1                                       |  |  |  |  |  |  |  |  |  |  |  |

|  |  |  |  |  |  |  |  |  |  |  |  |
|--|--|--|--|--|--|--|--|--|--|--|--|
| MECHANICAL PROPERTIES AS SUPPLIED (CONDITIONS)   |  |  |  |  |  |  |  |  |  |  |  |
| Specimen Test location: At 1/2 radius ; Temperature of: (1): Austenitizing 1.796 °F ; Time: (1): 120 Minutes |  |  |  |  |  |  |  |  |  |  |  |
| Cooling: (1): Oil 78/88 °F ; Temperature of: (2): Tempering 1.328 °F ; Time: (2): 120 Minutes                |  |  |  |  |  |  |  |  |  |  |  |
| Cooling: (2): Air ; Temperature of: (3): Stress Relieved 1.228 °F ; Time: (3): 360 Minutes                   |  |  |  |  |  |  |  |  |  |  |  |
| MECHANICAL PROPERTIES AS SUPPLIED (TEST)   |  |  |  |  |  |  |  |  |  |  |  |
| Standard(1) (ASTM A3702012A15.10.2012) ; Standard(2) (ASTM E8/E8M2013A01.07.2013)                            |  |  |  |  |  |  |  |  |  |  |  |
| Tensile test specimen direction (Longitudinal): Longitudinal ; Ts (95/120 KSI): 108 KSI                      |  |  |  |  |  |  |  |  |  |  |  |
| Ys (Rp(0,2%) 80/95 KSI): Rp(0,2%) 82 KSI ; El. ((4d) >= 20 %) : (4d) 26,8 % ; Z (>= 40 %) : 71,5 %           |  |  |  |  |  |  |  |  |  |  |  |
| Standard (ASTM E23-01AE12007) ; Notch impact sample direction (Longitudinal): Longitudinal                   |  |  |  |  |  |  |  |  |  |  |  |
| Notch Impact sample type (CHARPY-V): CHARPY-V ; Notch Impact test Temperature (14 °F): 14 °F                 |  |  |  |  |  |  |  |  |  |  |  |
| K(1): 103 Ft.Lb ; K(2): 102 Ft.Lb ; K(3): 100 Ft.Lb ; K (average) (>= 30 Ft.Lb): 102 Ft.Lb                   |  |  |  |  |  |  |  |  |  |  |  |
| K (single) (>= 25 Ft.Lb): 100 Ft.Lb ; Lateral expansion: 1.41-1.39-1.36 mm ; Shear value: 70-70-70 %         |  |  |  |  |  |  |  |  |  |  |  |
| Surface hardness (217/237 HBW): 226-230 HBW  |  |  |  |  |  |  |  |  |  |  |  |

|  |  |  |  |  |  |  |  |  |  |  |  |
|--|--|--|--|--|--|--|--|--|--|--|--|
| ADDITIONAL TESTS   |  |  |  |  |  |  |  |  |  |  |  |
| Structure: Ferrite Delta < 5% ; Standard (ASTM E112201301.10.2013) ; Grain size: 6 |  |  |  |  |  |  |  |  |  |  |  |
| radioactivity: FREE Bq/gr  |  |  |  |  |  |  |  |  |  |  |  |

|  |  |  |  |  |  |  |  |  |  |  |  |
|--|--|--|--|--|--|--|--|--|--|--|--|
| NON DESTRUCTIVE TESTS  |  |  |  |  |  |  |  |  |  |  |  |
| Surface defects standard (API SPEC 6A20*ED. +ER1&2+AD12.3. .03.2013) |  |  |  |  |  |  |  |  |  |  |  |
| Internal defects standard(1) (ASTM A388-A388M-. . .2011)             |  |  |  |  |  |  |  |  |  |  |  |

|  |  |  |  |  |  |                                 |  |  |  |  |  |
|--|--|--|--|--|--|---------------------------------|--|--|--|--|--|
| TECHNOLOGY & QUALITY CERTIFIES THAT THE PRODUCT FULL FILLS THE ORDER'S SPECIFICATION |  |  |  |  |  |                                 |  |  |  |  |  |
| APPROVED BY: MARCELINO GARCIA ZAYAS  |  |  |  |  |  | SIGN:                           |  |  |  |  |  |
| DATE: 28.10.2014   |  |  |  |  |  | Analyst of Quality certificates |  |  |  |  |  |
| REF.: 1002137540000  |  |  |  |  |  |                                 |  |  |  |  |  |

| Customer PO# | Sales Order# | Howco Disp Cert# | Date        | Authorized by  | Page No. | Total Pages |
|--------------|--------------|------------------|-------------|----------------|----------|-------------|
| 203298       | 2063728-1    | 2063728-1        | Jun 06 2017 | Megan McKeever | 1        | 2           |

## MILL TEST CERTIFICATE

Basauri Plant

ISO 9001 - ISO/TS 16949



Product Made in Spain

|  |                         |
|--|-------------------------|
| CUSTOMER:HOWCO METALS MANAGEMENT PTE LTD | WORKS REFERENCE:1740628 |
| REFERENCE:HOU-111769                     | SALES ORDER:273719-7    |
| PRODUCT NR:                              | HEAT NUMBER:629109      |
| MASTER REFERENCE:192526                  | ROLLED:03.07.2014       |

Internal defects standard(2) (API SPEC 6A20\*ED.+ER1&2+AD12.3. .03.2013)  
 Internal defects type/method(1) (FBH) ; Internal defects type/method(2) (PSL3) ; 1/8" (1)  
 S/API 6A(según cláusulas 7.4.2.3.15 y 7.4.2.4.11) (2) ; ULTRASONIC INSPECTION 100% : O.K. (1)  
 ULTRASONIC INSPECTION 100% : O.K. (2) ; CRACKS CONTROL 100%:OK

## ADDITIONAL INFORMATION

Reduction ratio:163,1 ; MADE IN ELECTRIC ARC FURNACE AND VACUUM DEGAISED.INGOT CAST 464 X 464 MM AVERAGE  
 TREATMENT TEMPERATURE MEASURED WITH ATMOSPHERIC THERMOCOUPLE  
 FURNACE CALIBRATION ACCORDING TO "API 6A appendix M" - AMS H-6875, AMS 2750  
 " NO WELD REPAIR PERFORMED " ; COUNTRY OF ORIGIN : SPAIN ; MATERIAL IS FREE OF MERCURY CONTAMINATION  
 TREATMENT OF THE MATERIAL IN CONVENTIONAL FURNACE  
 MECHANICAL PROPERTIES OBTAINED FROM PROLONGATION OF THE BAR AFTER HEAT TREATMENT ; ACC. TO ASTM A370.  
 . . . .  
 The mill supply chain controls have taken into account Dodd Frank Act requirements regarding conflict minerals.

TECHNOLOGY &amp; QUALITY CERTIFIES THAT THE PRODUCT FULL FILLS THE ORDER'S SPECIFICATION

APPROVED BY:MARCELINO GARCIA ZAYAS

SIGN:

DATE:28.10.2014

Page 2 of 2

REF.:1002137540000

Analyst of Quality certificates

| Customer PO# | Sales Order# | Howco Disp Cert# | Date        | Authorized by  | Page No. | Total Pages |
|--------------|--------------|------------------|-------------|----------------|----------|-------------|
| 203298       | 2063728-1    | 2063728-1        | Jun 06 2017 | Megan McKeever | 2        | 2           |